

Miescher-Elementarfarben (e) von maximaler (m) C* _{ab} ; C00, λ _d =574nm, CIEXYZ													
Code, K=1:25	X	Y	Z	x	y	z	h _{xy}	i _d	λ _d	i _c	λ _c		
R _{e,C}	CIE 09	2.12	1.15	0.47	0.5672	0.3068	0.1258	225.8	43 618	17 486			
Y _{e,C}	CIE 10	5.59	5.9	1.28	0.4378	0.4618	0.1003	225.4	34 570	14 470			
G _{e,C}	CIE 11	1.24	2.0	1.64	0.2544	0.409	0.3364	225.3	21 507	-1 507c			
B _{e,C}	CIE 12	0.66	0.64	2.96	0.155	0.1512	0.6937	225.5	14 471	34 571			
R _{e,M}	MIE 20	2.12	1.15	0.47	0.5672	0.3068	0.1258	225.8	43 618	17 486			
Y _{e,M}	MIE 02	5.59	5.9	1.28	0.4378	0.4618	0.1003	225.4	34 570	14 470			
G _{e,M}	MIE 08	1.24	2.0	1.64	0.2544	0.409	0.3364	225.3	21 507	-1 507c			
B _{e,M}	MIE 14	0.66	0.64	2.96	0.155	0.1512	0.6937	225.5	14 471	34 571			
W	380_770	88.26	90.0	106.4	0.31	0.3161	0.3737	225.5	-1 573c	34 573			
N	380_770	0.35	0.36	0.42	0.31	0.3161	0.3737	225.5	14 471	34 573			

EG750-1A C00

Miescher-Elementarfarben (e) von maximaler (m) C* _{ab} ; C00, λ _d =574nm, YAB_77													
Code, K=1:25	Y	A	B	C _{AB}	a	b	h _{AB}	i _d	λ* _d	i _c	λ* _c		
R _{e,C}	CIE 09	1.15	0.99	0.35	1.06	1.8485	-0.164	19.5	42 614	17 485			
Y _{e,C}	CIE 10	5.9	-0.19	2.27	2.28	0.948	-0.0869	94.8	34 570	14 471			
G _{e,C}	CIE 11	2.0	-0.71	0.28	0.77	0.6221	-0.329	158.1	24 521	-1 521c			
B _{e,C}	CIE 12	0.64	0.02	-0.87	0.87	1.025	-1.8348	271.8	14 471	34 570			
R _{e,M}	MIE 20	1.15	0.99	0.35	1.06	1.8485	-0.164	19.5	42 614	17 485			
Y _{e,M}	MIE 02	5.9	-0.19	2.27	2.28	0.948	-0.0869	94.8	34 570	14 471			
G _{e,M}	MIE 08	2.0	-0.71	0.28	0.77	0.6221	-0.329	158.1	24 521	-1 521c			
B _{e,M}	MIE 14	0.64	0.02	-0.87	0.87	1.025	-1.8348	271.8	14 471	34 570			
W	380_770	90.0	0.0	0.0	0.01	0.9807	-0.4729	358.3	35 576	15 476			
N	380_770	0.36	0.0	0.0	0.01	0.9804	-0.4727	87.1	35 576	15 476			

EG750-3A C00

Miescher-Elementarfarben (e) von maximaler (m) C* _{ab} ; C00, λ _d =574nm, CIELAB_76													
Code, K=1:25	L*	a*	b*	C* _{ab}	a'	b'	h _{ab}	i _d	λ* _d	i _c	λ* _c		
R _{e,C}	CIE 09	10.26	26.45	10.34	28.4	0.2661	-0.0605	21.3	-1 482c	16 482			
Y _{e,C}	CIE 10	29.19	-2.18	33.5	33.57	0.213	-0.049	93.7	33 569	14 471			
G _{e,C}	CIE 11	15.56	-19.03	6.16	20.0	0.1851	-0.0763	162.0	22 511	-1 511c			
B _{e,C}	CIE 12	5.83	1.14	-20.95	20.98	0.2186	-0.1354	273.1	14 471	34 570			
R _{e,M}	MIE 20	10.26	26.45	10.34	28.4	0.2661	-0.0605	21.3	-1 482c	16 482			
Y _{e,M}	MIE 02	29.19	-2.18	33.5	33.57	0.213	-0.049	93.7	33 569	14 471			
G _{e,M}	MIE 08	15.56	-19.03	6.16	20.0	0.1851	-0.0763	162.0	22 511	-1 511c			
B _{e,M}	MIE 14	5.83	1.14	-20.95	20.98	0.2186	-0.1354	273.1	14 471	34 570			
W	380_770	96.0	0.0	0.0	0.0	0.2154	-0.0861	274.7	14 472	34 572			
N	380_770	3.25	0.0	-1.02	1.02	0.2154	-0.0861	270.0	14 472	34 572			

EG750-5A C00

Miescher-Elementarfarben (e) von maximaler (m) C* _{ab} ; C00, λ _d =574nm, LABHNU1_79													
Code, K=1:25	L*	A*	B*	C* _{ab}	a'	b'	h _{ab}	i _d	λ* _d	i _c	λ* _c		
R _{e,C}	CIE 09	10.26	30.31	11.89	32.56	0.1899	-0.0693	21.4	54 674	16 484			
Y _{e,C}	CIE 10	29.19	-1.97	28.46	28.53	0.1298	-0.0605	93.9	34 570	14 471			
G _{e,C}	CIE 11	15.56	-15.06	5.69	16.1	0.1081	-0.083	159.2	20 503	8 443			
B _{e,C}	CIE 12	5.83	1.27	-20.75	20.79	0.135	-0.1401	273.5	14 471	34 570			
R _{e,M}	MIE 20	10.26	30.31	11.89	32.56	0.1899	-0.0693	21.4	54 674	16 484			
Y _{e,M}	MIE 02	29.19	-1.97	28.46	28.53	0.1298	-0.0605	93.9	34 570	14 471			
G _{e,M}	MIE 08	15.56	-15.06	5.69	16.1	0.1081	-0.083	159.2	20 503	8 443			
B _{e,M}	MIE 14	5.83	1.27	-20.75	20.79	0.135	-0.1401	273.5	14 471	34 570			
W	380_770	96.0	0.0	0.0	0.0	0.132	-0.092	350.5	14 472	34 572			
N	380_770	3.25	0.0	0.0	0.0	0.132	-0.092	157.3	20 504	9 445			

EG750-7A C00

EG750-7N C00