




CIE data for antichromatic optimal colours of maximum chromatic value for D65. $Y_w=100$. $Y_m=520\ 770$. $B_m=380\ 520$




CIE data for antichromatic optimal colours of maximum chromatic value for D50, $Y_w=100$, $Y_m=520.770$, $B_m=380.520$




CIE data for antichromatic optimal colours of maximum chromatic value for P40. $Y_w=100$. $Y_m=520\ 770$. $B_m=380\ 520$



CIE data for antichromatic optimal colours of maximum chromatic value for A00, $Y_m=100$, $Y_m=520\ 770$, $B_m=380\ 520$




CIE data for antichromatic optimal colours of maximum chromatic value for E00, $Y_w=100$, $Y_m=520.770$, $B_m=380.520$



CIE data for antichromatic optimal colours of maximum chromatic value for C00, $Y_m=100$, $Y_m=520\ 770$, $B_m=380\ 520$


**CIE tristimulus values X , Y , Z
in the range $Y=0$ to 100**




4-000030-L0

SI840-7A_1

CIE data for antichromatic optimal colours of maximum chromatic value for P00. $Y_w=100$. $Y_m=520\ 770$. $B_m=380\ 520$



CIE data for antichromatic optimal colours of maximum chromatic value for O00. $Y_n=100$. $Y_m=520\ 770$. $B_m=380\ 520$



4-000030-L0

SI840-7A_1