

i	LAB*ref		l*out		LAB*out		LAB*out/c-ref			$\Delta E^*$	<b>Start output S1</b>
1	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.01	<b>Specification according to ISO/IEC 15775 Annex G and DIN 33866-1 Annex G</b>
2	6.36	0.0	0.0	0.07	6.36	0.0	0.0	0.0	0.0	0.01	
3	12.72	0.0	0.0	0.13	12.72	0.0	0.0	0.0	0.0	0.01	
4	19.08	0.0	0.0	0.2	19.08	0.0	0.0	0.0	0.0	0.01	
5	25.44	0.0	0.0	0.27	25.44	0.0	0.0	0.0	0.0	0.01	
6	31.8	0.0	0.0	0.33	31.8	0.0	0.0	0.0	0.0	0.01	
7	38.16	0.0	0.0	0.4	38.16	0.0	0.0	0.0	0.0	0.01	
8	44.52	0.0	0.0	0.47	44.52	0.0	0.0	0.0	0.0	0.01	
9	50.89	0.0	0.0	0.53	50.89	0.0	0.0	0.0	0.0	0.01	
10	57.25	0.0	0.0	0.6	57.25	0.0	0.0	0.0	0.0	0.01	
11	63.61	0.0	0.0	0.67	63.61	0.0	0.0	0.0	0.0	0.01	
12	69.97	0.0	0.0	0.73	69.97	0.0	0.0	0.0	0.0	0.01	
13	76.33	0.0	0.0	0.8	76.33	0.0	0.0	0.0	0.0	0.01	
14	82.69	0.0	0.0	0.87	82.69	0.0	0.0	0.0	0.0	0.01	
15	89.05	0.0	0.0	0.93	89.05	0.0	0.0	0.0	0.0	0.01	
16	95.41	0.0	0.0	1.0	95.41	0.0	0.0	0.0	0.0	0.01	$\Delta E^*_{\text{CIELAB}} = 0.0$
17	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.01	
18	23.85	0.0	0.0	0.25	23.85	0.0	0.0	0.0	0.0	0.01	
19	47.71	0.0	0.0	0.5	47.71	0.0	0.0	0.0	0.0	0.01	
20	71.56	0.0	0.0	0.75	71.56	0.0	0.0	0.0	0.0	0.01	<b>Mean lightness difference (5 steps)</b>
21	95.41	0.0	0.0	1.0	95.41	0.0	0.0	0.0	0.0	0.01	$\Delta L^*_{\text{CIELAB}} = 0.0$
<b>Mean colour reproduction index:</b>									$R^*_{\text{ab,m}} = 100$		

i	LAB*ref		l*out		LAB*out		LAB*out/c-ref			$\Delta E^*$	<b>Start output S1</b>
1	5.69	0.0	0.0	0.0	5.69	0.0	0.0	0.0	0.0	0.01	<b>Specification according to ISO/IEC 15775 Annex G and DIN 33866-1 Annex G</b>
2	11.67	0.0	0.0	0.1	14.73	0.0	0.0	3.06	0.0	3.06	
3	17.65	0.0	0.0	0.18	21.96	0.0	0.0	4.3	0.0	4.3	
4	23.63	0.0	0.0	0.26	28.63	0.0	0.0	4.99	0.0	4.99	
5	29.62	0.0	0.0	0.33	34.96	0.0	0.0	5.34	0.0	5.34	
6	35.6	0.0	0.0	0.39	41.05	0.0	0.0	5.46	0.0	5.46	
7	41.58	0.0	0.0	0.46	46.96	0.0	0.0	5.38	0.0	5.38	
8	47.56	0.0	0.0	0.52	52.72	0.0	0.0	5.16	0.0	5.16	
9	53.54	0.0	0.0	0.59	58.36	0.0	0.0	4.82	0.0	4.82	
10	59.52	0.0	0.0	0.65	63.88	0.0	0.0	4.36	0.0	4.36	
11	65.5	0.0	0.0	0.71	69.32	0.0	0.0	3.82	0.0	3.82	
12	71.48	0.0	0.0	0.77	74.67	0.0	0.0	3.19	0.0	3.19	
13	77.47	0.0	0.0	0.83	79.95	0.0	0.0	2.49	0.0	2.49	
14	83.45	0.0	0.0	0.89	85.16	0.0	0.0	1.72	0.0	1.72	
15	89.43	0.0	0.0	0.94	90.31	0.0	0.0	0.89	0.0	0.89	
16	95.41	0.0	0.0	1.0	95.41	0.0	0.0	0.0	0.0	0.01	$\Delta E^*_{\text{CIELAB}} = 3.4$
17	5.69	0.0	0.0	0.0	5.69	0.0	0.0	0.0	0.0	0.01	
18	28.12	0.0	0.0	0.31	33.4	0.0	0.0	5.28	0.0	5.28	
19	50.55	0.0	0.0	0.56	55.55	0.0	0.0	5.0	0.0	5.0	
20	72.98	0.0	0.0	0.78	76.0	0.0	0.0	3.02	0.0	3.02	<b>Mean lightness difference (5 steps)</b>
21	95.41	0.0	0.0	1.0	95.41	0.0	0.0	0.0	0.0	0.01	$\Delta L^*_{\text{CIELAB}} = 2.7$
<b>Mean colour reproduction index:</b>									$R^*_{\text{ab,m}} = 85$		

i	LAB*ref		l*out		LAB*out		LAB*out/c-ref			$\Delta E^*$	<b>Start output S1</b>	
1	10.99	0.0	0.0	0.0	10.99	0.0	0.0	0.0	0.0	0.01	<b>Specification according to ISO/IEC 15775 Annex G and DIN 33866-1 Annex G</b>	
2	16.62	0.0	0.0	0.14	22.52	0.0	0.0	5.9	0.0	5.9		
3	22.25	0.0	0.0	0.23	30.18	0.0	0.0	7.93	0.0	7.93		
4	27.88	0.0	0.0	0.31	36.84	0.0	0.0	8.97	0.0	8.97		
5	33.5	0.0	0.0	0.38	42.93	0.0	0.0	9.43	0.0	9.43		
6	39.13	0.0	0.0	0.45	48.63	0.0	0.0	9.5	0.0	9.5		
7	44.76	0.0	0.0	0.51	54.03	0.0	0.0	9.27	0.0	9.27		
8	50.39	0.0	0.0	0.57	59.19	0.0	0.0	8.81	0.0	8.81		
9	56.02	0.0	0.0	0.63	64.17	0.0	0.0	8.15	0.0	8.15		
10	61.64	0.0	0.0	0.69	68.98	0.0	0.0	7.33	0.0	7.33		
11	67.27	0.0	0.0	0.74	73.65	0.0	0.0	6.38	0.0	6.38		
12	72.9	0.0	0.0	0.8	78.2	0.0	0.0	5.3	0.0	5.3		
13	78.53	0.0	0.0	0.85	82.64	0.0	0.0	4.11	0.0	4.11		
14	84.15	0.0	0.0	0.9	86.98	0.0	0.0	2.82	0.0	2.82		
15	89.78	0.0	0.0	0.95	91.23	0.0	0.0	1.45	0.0	1.45		<b>Mean lightness difference (16 steps)</b>
16	95.41	0.0	0.0	1.0	95.41	0.0	0.0	0.0	0.0	0.01		$\Delta E^*_{\text{CIELAB}} = 6.0$
17	10.99	0.0	0.0	0.0	10.99	0.0	0.0	0.0	0.0	0.01		
18	32.1	0.0	0.0	0.36	41.45	0.0	0.0	9.36	0.0	9.36		
19	53.2	0.0	0.0	0.6	61.7	0.0	0.0	8.5	0.0	8.5		
20	74.31	0.0	0.0	0.81	79.32	0.0	0.0	5.01	0.0	5.01		<b>Mean lightness difference (5 steps)</b>
21	95.41	0.0	0.0	1.0	95.41	0.0	0.0	0.0	0.0	0.01		$\Delta L^*_{\text{CIELAB}} = 4.6$
<b>Mean colour reproduction index:</b>									$R^*_{\text{ab,m}} = 74$			

i	LAB*ref		l*out	LAB*out			LAB*out/c-ref		$\Delta E^*$	<b>Start output S1</b>
1	18.01	0.0	0.0	0.0	18.01	0.0	0.0	0.0	0.01	<b>Specification according to</b>
2	23.17	0.0	0.0	0.17	31.35	0.0	0.0	8.18	0.0	<b>ISO/IEC 15775 Annex G</b>
3	28.33	0.0	0.0	0.27	38.93	0.0	0.0	10.6	0.0	<b>and DIN 33866-1 Annex G</b>
4	33.49	0.0	0.0	0.35	45.23	0.0	0.0	11.74	0.0	
5	38.65	0.0	0.0	0.42	50.82	0.0	0.0	12.17	0.0	
6	43.81	0.0	0.0	0.49	55.93	0.0	0.0	12.12	0.0	
7	48.97	0.0	0.0	0.55	60.7	0.0	0.0	11.73	0.0	
8	54.13	0.0	0.0	0.61	65.2	0.0	0.0	11.07	0.0	
9	59.29	0.0	0.0	0.66	69.47	0.0	0.0	10.18	0.0	
10	64.45	0.0	0.0	0.72	73.56	0.0	0.0	9.11	0.0	
11	69.61	0.0	0.0	0.77	77.49	0.0	0.0	7.88	0.0	
12	74.77	0.0	0.0	0.82	81.29	0.0	0.0	6.52	0.0	
13	79.93	0.0	0.0	0.87	84.97	0.0	0.0	5.04	0.0	
14	85.09	0.0	0.0	0.91	88.54	0.0	0.0	3.45	0.0	
15	90.25	0.0	0.0	0.96	92.02	0.0	0.0	1.77	0.0	<b>Mean lightness difference (16 steps)</b>
16	95.41	0.0	0.0	1.0	95.41	0.0	0.0	0.0	0.01	$\Delta E^*_{\text{CIELAB}} = 7.6$
17	18.01	0.0	0.0	0.0	18.01	0.0	0.0	0.0	0.0	
18	37.36	0.0	0.0	0.41	49.47	0.0	0.0	12.11	0.0	
19	56.71	0.0	0.0	0.64	67.36	0.0	0.0	10.65	0.0	
20	76.06	0.0	0.0	0.83	82.22	0.0	0.0	6.16	0.0	<b>Mean lightness difference (5 steps)</b>
21	95.41	0.0	0.0	1.0	95.41	0.0	0.0	0.0	0.01	$\Delta L^*_{\text{CIELAB}} = 5.8$
<b>Mean colour reproduction index:</b>									$R^*_{\text{ab,m}} = 67$	

i	LAB*ref		l*out		LAB*out		LAB*out/c-ref			$\Delta E^*$	<b>Start output S1</b>	
1	26.85	0.0	0.0	0.0	26.85	0.0	0.0	0.0	0.0	0.01	<b>Specification according to ISO/IEC 15775 Annex G and DIN 33866-1 Annex G</b>	
2	31.42	0.0	0.0	0.21	41.05	0.0	0.0	9.63	0.0	9.63		
3	35.99	0.0	0.0	0.31	48.1	0.0	0.0	12.11	0.0	12.11		
4	40.56	0.0	0.0	0.39	53.75	0.0	0.0	13.18	0.0	13.18		
5	45.13	0.0	0.0	0.46	58.64	0.0	0.0	13.51	0.0	13.51		
6	49.7	0.0	0.0	0.53	63.05	0.0	0.0	13.34	0.0	13.34		
7	54.27	0.0	0.0	0.59	67.09	0.0	0.0	12.82	0.0	12.82		
8	58.84	0.0	0.0	0.64	70.87	0.0	0.0	12.02	0.0	12.02		
9	63.41	0.0	0.0	0.69	74.42	0.0	0.0	11.01	0.0	11.01		
10	67.99	0.0	0.0	0.74	77.79	0.0	0.0	9.81	0.0	9.81		
11	72.56	0.0	0.0	0.79	81.01	0.0	0.0	8.46	0.0	8.46		
12	77.13	0.0	0.0	0.84	84.1	0.0	0.0	6.97	0.0	6.97		
13	81.7	0.0	0.0	0.88	87.07	0.0	0.0	5.37	0.0	5.37		
14	86.27	0.0	0.0	0.92	89.94	0.0	0.0	3.67	0.0	3.67		
15	90.84	0.0	0.0	0.96	92.71	0.0	0.0	1.88	0.0	1.88		<b>Mean lightness difference (16 steps)</b>
16	95.41	0.0	0.0	1.0	95.41	0.0	0.0	0.0	0.0	0.01		$\Delta E^*_{\text{CIELAB}} = 8.4$
17	26.85	0.0	0.0	0.0	26.85	0.0	0.0	0.0	0.0	0.01		
18	43.99	0.0	0.0	0.45	57.47	0.0	0.0	13.48	0.0	13.48		
19	61.13	0.0	0.0	0.67	72.67	0.0	0.0	11.54	0.0	11.54		
20	78.27	0.0	0.0	0.85	84.85	0.0	0.0	6.58	0.0	6.58		<b>Mean lightness difference (5 steps)</b>
21	95.41	0.0	0.0	1.0	95.41	0.0	0.0	0.0	0.0	0.01		$\Delta L^*_{\text{CIELAB}} = 6.3$
<b>Mean colour reproduction index:</b>								$R^*_{\text{ab,m}} = 64$				

i	LAB*ref	l*out	LAB*out	LAB*out/c-ref	$\Delta E^*$	<b>Start output S1</b>
1	37.99 0.0	0.0	0.0	37.99 0.0	0.0	<b>Specification according to</b>
2	41.81 0.0	0.0	0.24	51.79 0.0	0.0	<b>ISO/IEC 15775 Annex G</b>
3	45.64 0.0	0.0	0.35	57.87 0.0	0.0	<b>and DIN 33866-1 Annex G</b>
4	49.47 0.0	0.0	0.43	62.6 0.0	0.0	
5	53.3 0.0	0.0	0.5	66.63 0.0	0.0	
6	57.13 0.0	0.0	0.56	70.19 0.0	0.0	
7	60.96 0.0	0.0	0.62	73.44 0.0	0.0	
8	64.78 0.0	0.0	0.67	76.44 0.0	0.0	
9	68.61 0.0	0.0	0.72	79.23 0.0	0.0	
10	72.44 0.0	0.0	0.76	81.87 0.0	0.0	
11	76.27 0.0	0.0	0.81	84.37 0.0	0.0	
12	80.1 0.0	0.0	0.85	86.76 0.0	0.0	
13	83.93 0.0	0.0	0.89	89.05 0.0	0.0	
14	87.75 0.0	0.0	0.93	91.24 0.0	0.0	
15	91.58 0.0	0.0	0.96	93.36 0.0	0.0	<b>Mean lightness difference (16 steps)</b>
16	95.41 0.0	0.0	1.0	95.41 0.0	0.0	$\Delta E^*_{\text{CIELAB}} = 8.2$
17	37.99 0.0	0.0	0.0	37.99 0.0	0.0	
18	52.34 0.0	0.0	0.48	65.67 0.0	0.0	
19	66.7 0.0	0.0	0.69	77.86 0.0	0.0	
20	81.05 0.0	0.0	0.86	87.34 0.0	0.0	<b>Mean lightness difference (5 steps)</b>
21	95.41 0.0	0.0	1.0	95.41 0.0	0.0	$\Delta L^*_{\text{CIELAB}} = 6.2$
<b>Mean colour reproduction index:</b>					$R^*_{\text{ab,m}} = 65$	

i	LAB*ref	l*out	LAB*out	LAB*out/c-ref	$\Delta E^*$	Start output S1
1	52.02 0.0	0.0	0.0	52.02 0.0	0.0	<b>Specification according to</b>
2	54.91 0.0	0.0	0.27	63.82 0.0	0.0	<b>ISO/IEC 15775 Annex G</b>
3	57.8 0.0	0.0	0.38	68.49 0.0	0.0	<b>and DIN 33866-1 Annex G</b>
4	60.7 0.0	0.0	0.46	72.03 0.0	0.0	
5	63.59 0.0	0.0	0.53	75.0 0.0	0.0	
6	66.48 0.0	0.0	0.59	77.61 0.0	0.0	
7	69.37 0.0	0.0	0.64	79.95 0.0	0.0	
8	72.27 0.0	0.0	0.69	82.1 0.0	0.0	
9	75.16 0.0	0.0	0.74	84.09 0.0	0.0	
10	78.05 0.0	0.0	0.78	85.96 0.0	0.0	
11	80.95 0.0	0.0	0.82	87.72 0.0	0.0	
12	83.84 0.0	0.0	0.86	89.4 0.0	0.0	
13	86.73 0.0	0.0	0.9	91.0 0.0	0.0	
14	89.62 0.0	0.0	0.93	92.53 0.0	0.0	
15	92.52 0.0	0.0	0.97	93.99 0.0	0.0	1.48 <b>Mean lightness difference (16 steps)</b>
16	95.41 0.0	0.0	1.0	95.41 0.0	0.0	0.0 <b><math>\Delta E^*_{\text{CIELAB}} = 7.0</math></b>
17	52.02 0.0	0.0	0.0	52.02 0.0	0.0	0.0 0.01
18	62.87 0.0	0.0	0.51	74.3 0.0	0.0	11.43 0.0 11.43
19	73.71 0.0	0.0	0.72	83.11 0.0	0.0	9.4 0.0 9.4
20	84.56 0.0	0.0	0.87	89.81 0.0	0.0	5.24 0.0 5.24 <b>Mean lightness difference (5 steps)</b>
21	95.41 0.0	0.0	1.0	95.41 0.0	0.0	0.0 0.0 0.01 <b><math>\Delta L^*_{\text{CIELAB}} = 5.2</math></b>
<b>Mean colour reproduction index:</b>					<b><math>R^*_{\text{ab,m}} = 70</math></b>	

i	LAB*ref		l*out		LAB*out		LAB*out/c-ref			$\Delta E^*$	<b>Start output S1</b>	
1	69.7	0.0	0.0	0.0	69.7	0.0	0.0	0.0	0.0	0.01	<b>Specification according to ISO/IEC 15775 Annex G and DIN 33866-1 Annex G</b>	
2	71.41	0.0	0.0	0.3	77.46	0.0	0.0	6.04	0.0	6.04		
3	73.13	0.0	0.0	0.41	80.24	0.0	0.0	7.11	0.0	7.11		
4	74.84	0.0	0.0	0.49	82.31	0.0	0.0	7.47	0.0	7.47		
5	76.55	0.0	0.0	0.56	84.02	0.0	0.0	7.47	0.0	7.47		
6	78.27	0.0	0.0	0.62	85.51	0.0	0.0	7.24	0.0	7.24		
7	79.98	0.0	0.0	0.67	86.84	0.0	0.0	6.86	0.0	6.86		
8	81.7	0.0	0.0	0.71	88.05	0.0	0.0	6.35	0.0	6.35		
9	83.41	0.0	0.0	0.76	89.17	0.0	0.0	5.76	0.0	5.76		
10	85.12	0.0	0.0	0.8	90.21	0.0	0.0	5.08	0.0	5.08		
11	86.84	0.0	0.0	0.84	91.19	0.0	0.0	4.35	0.0	4.35		
12	88.55	0.0	0.0	0.87	92.11	0.0	0.0	3.56	0.0	3.56		
13	90.27	0.0	0.0	0.91	92.99	0.0	0.0	2.73	0.0	2.73		
14	91.98	0.0	0.0	0.94	93.83	0.0	0.0	1.85	0.0	1.85		
15	93.7	0.0	0.0	0.97	94.64	0.0	0.0	0.94	0.0	0.94		<b>Mean lightness difference (16 steps)</b>
16	95.41	0.0	0.0	1.0	95.41	0.0	0.0	0.0	0.0	0.01		$\Delta E^*_{\text{CIELAB}} = 4.6$
17	69.7	0.0	0.0	0.0	69.7	0.0	0.0	0.0	0.0	0.01		
18	76.13	0.0	0.0	0.54	83.62	0.0	0.0	7.5	0.0	7.5		
19	82.55	0.0	0.0	0.74	88.62	0.0	0.0	6.06	0.0	6.06		
20	88.98	0.0	0.0	0.88	92.34	0.0	0.0	3.35	0.0	3.35		<b>Mean lightness difference (5 steps)</b>
21	95.41	0.0	0.0	1.0	95.41	0.0	0.0	0.0	0.0	0.01		$\Delta L^*_{\text{CIELAB}} = 3.4$
<b>Mean colour reproduction index:</b>									$R^*_{\text{ab,m}} = 80$			